

FONDOVALLE

Technical characteristics according to international standards for CERAMIC TILES, UNI EN ISO 14411: 2016

Requirements of Group BIa UGL

Series REFLEX (Thickness 6 mm)

Technical characteristics	Test methods	Requirements EN 14411	Fondovalle Values	
			L < 120 cm	L ≥ 120 cm
 Length and Width Average deviation (%) of each tile by the size of production Thickness Straightness of the edges Rectangularity Planarity Surface quality	UNI EN ISO 10545-2	± 0,6%	± 0,6%	± 0,6%
		± 2 mm	± 0,5 mm	± 0,9 mm
		± 5%	± 5%	± 3%
		± 0,5 mm	± 0,5 mm	± 0,5 mm
		± 0,5%	± 0,5%	± 0,5%
		± 1,5 mm	± 1,5 mm	± 1,5 mm
		± 0,5%	± 0,5%	± 0,5%
 Water absorption	UNI EN ISO 10545-3	≤ 0,5%	≤ 0.1%	Compliant
		 Modulus of rupture Breaking strength	R Average ≥ 35 N/mm ² R Minimum ≥ 32N/mm ²	h = 6 mm; R ≥ 50 N/mm ²
 Resistance to deep abrasion	UNI EN ISO 10545-6		V ≤ 175 mm ³	h = 6 mm; V ≤ 130 mm ³
		 Resistance to thermal chock	UNI EN ISO 10545-9	Resistant
 Frost resistance	UNI EN ISO 10545-12			Resistant
		 Chemical Resistance	UNI EN ISO 10545-13	Declared values; B minimum
 Stain resistance	UNI EN ISO 10545-14			Minimum Class 3
		 Resistance of colors to light	DIN 51094	Resistant
 Fire Reaction	UNI EN 13501-1			Resistant

* Stated values are obtained from laboratory tests. They may vary depending on the production batch.

COMPLIANCE FOR
FOOD CONTACT
MATERIAL
(Conformità MOCA)

